

DESCRIPTION

| | | | |
|-----------------------------|--------------------------|-------------|--------|
| Total thickness | EN ISO 24346 [EN 428] | mm | 1.5 |
| | ASTM F386-02 | inch | 0.06 |
| Weight | EN ISO 23997 [EN 430] | g/sq.m | 2520 |
| Width of sheet | EN ISO 24341 [EN 426] | cm | 200 |
| | - | feet - inch | 6'6" |
| Length of sheet | EN ISO 24341 [EN 426] | lm | 20 |
| | - | feet - inch | 66' |
| Coverage / roll | - | sq.ft | 430.56 |
| | - | sq.m | 40 |
| Tile size | EN ISO 24342 [EN 427] | mm | - |
| Number of tiles per package | - | - | - |

CLASSIFICATION

| | | | |
|------------------------------|--------------------------|-------|-----------------------|
| Norm / Product specification | - | - | EN ISO 10581 (EN 649) |
| European classification | EN ISO 10874 (EN 685) | class | 23-31 |
| Fire rating | EN 13 501-1 | class | B _{fl} -s1 |
| Static electrical propensity | EN 1815 | kV | < 2 |






PERFORMANCE

| | | | |
|------------------------------|----------------------------|-----------------|--------|
| Wear resistance | EN 660.2 | mm ³ | ≤ 15 |
| Wear Group | (EN 649) | group | F |
| Type Binder content | EN ISO 10581 | type | II |
| Dimensional stability | EN ISO 23999 [EN 434] | % | ≤ 0.40 |
| Residual indentation | EN ISO 24343-1 [EN 433] | mm | ≈ 0.03 |
| Castor chair test (type W) | ISO 4918 (EN 425) | - | OK |
| Thermal conductivity | EN ISO 10456 (EN12524) | W/(m.K) | 0.25 |
| Colour fastness | EN 20 105 - B02 | degree | ≥ 6 |
| Surface treatment | - | - | PUR |
| Chemical products resistance | EN ISO 26987 [EN 423] | class | OK |

ENVIRONMENT / INDOOR AIR QUALITY

| | | | |
|--------------------|-------------|--------------------|------|
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 10 |
|--------------------|-------------|--------------------|------|

CE MARKING

| | | | |
|--|----------|---|--|
|  | EN 14041 | - |    |
| | | - |  |